



## CaTop M 170 + G (SK) UDB $(\in 11 \nearrow 10^{10})$



## **CaTop M 170 + G (SK)**



## SYSTEMATIC SAFETY AND ENERGY EFFICIENCY



CaTop M 170 + G SK is a diffusion permeable, universally applicable and highly tear-resistant sarking and underlay membrane, in accordance DIN EN 13859-1, equipped with two integrated self-adhesive strips. Also available without adhesive strips, as CaTop M 170 + G. The multi-layered membrane consists of polypropylene woven material, a medium reinforced fabric and an inner-lying functional membrane. Also suitable as a temporary covering roof membrane. The special design gives it an exceptionally high tear resistance and good rainwater tightness, while simultaneously having a high water-vapour permeability.

When working with the material it is necessary to observe the applicable standards, the generally recognized rules of manufacturers as well as the CaPlast laying information. Subject to technical modifications.

FIELDS OF APPLICATION	TECHNICAL DATA	
Sarking (UDB) and underlay (USB)	Weight (g/m²)	195 ± 10%
Femporary roof covering	Building material	Е
Formwork membrane	Resistance to water penetration	W 1
Rear ventilated and non rear ventilated constructions	s <sub>d</sub> -value (m)	$0.04 \pm 0.02$
Renovation work and new constructions	Resistance to water pressure (cm WS)	> 400
	Tear resistance L/T (N/5 cm)	500/410 ± 50
BENEFITS	Elongation L/T (%)	18/15 ± 5
tegrated self adhesive strips	Nail tear resistance L/T (N)	440/430 ± 40
pproved sealing against driving rain	Temperature resistance (°C)	- 40 to + 80
ery good tear resistance and nail tear resistance	Temporary roof covering (weeks)	4
ligh diffusion permeability	Roll width/Roll length (m)	1.50/50
npervious to wind, water and driving rain		
Secure laying and easy handling		

CaPlast Kunststoffverarbeitungs GmbH Magdheide 7 - D-59394 Nordkirchen, Germany Phone: +49 25 99/913-0 Fax: +49 25 99/913-33 e-mail: info@caplast.de www.caplast.de